

Abstract

In order to improve castability of a titanium alloy, 0.01-5 wt%, preferably 0.1-3 wt%, of bismuth is introduced into the titanium alloy, based on the weight of bismuth and the titanium alloy. The titanium alloy is suitable for making a
5 dental casting or a medical implant by casting.